

## Characterization of mid- and long term emissions from building materials: impact of use and wear conditions

M. Nicolas, B. d'Anna, Alexandre Albinet, François Maupetit, Laura

Chiappini

#### ► To cite this version:

M. Nicolas, B. d'Anna, Alexandre Albinet, François Maupetit, Laura Chiappini. Characterization of mid- and long term emissions from building materials: impact of use and wear conditions. 14. International Conference on Indoor Air Quality and Climate (Indoor Air 2016), Jul 2016, Ghent, Belgium. ineris-01863024

### HAL Id: ineris-01863024 https://ineris.hal.science/ineris-01863024

Submitted on 28 Aug 2018

**HAL** is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers. L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

# Characterization of mid- and long term emissions from building materials: impact of use and wear conditions

Mélanie NICOLAS<sup>1\*</sup>, Barbara D'ANNA<sup>2</sup>, Laura CHIAPPINI<sup>3</sup>, Alexandre ALBINET<sup>3</sup>, and François MAUPETIT<sup>1</sup>

 1 CSTB (Centre Scientifique et Technique du Bâtiment), Saint-Martin d'Hères, France
2 IRCELYON (Institut de Recherches sur la Catalyse et l'Environnement de Lyon), University Claude Bernard Lyon 1, Lyon, Rhône-Alpes, France
3 INERIS (Institut National de l'Environnement industriel et des RISques), Parc technologique Alata, BP 2, 60550 Verneuil-en-Halatte, France

Corresponding author: melanie.nicolas@cstb.fr

#### SUMMARY

Indoor emissions from building products are conventionally characterized on new products. But ageing of building products in use in real buildings can change their surface properties and their emissions into indoor air. The aim of this research project was to characterize the impact of wear conditions and use of building products on their middle and long-term indoor emissions. For specific scenarios, in particular those involving oxidation and high relative humidity exposure, significant modifications of VOCs emissions were observed compared to new products.

#### **KEYWORDS**

Building products, emission, VOCs, formaldehyde, use, ageing

#### **1 INTRODUCTION**

Indoor emissions from building products are conventionally characterized on new products. But ageing of building products in use in real buildings can change their surface properties and their emissions into indoor air. Although ozone induced surface reactivity on building materials has been identified and studied since the 90s (Weschler et al. 1992; Reiss et al. 1995; Lee et al. 1996), studies on the influence of surface reactivity on emissions of pollutants in indoor air remain scarce.

The aim of this research project was to characterize the impact of wear conditions and use of building products on their middle and long-term emissions indoors. Therefore, short-term emissions of new building products will be compared to their mid- and long-term emissions characterized through various scenarios of ageing.

#### 2 MATERIALS/METHODS

One of the key points of this work was the definition of relevant ageing scenarios representative of realistic indoor conditions. Relevant parameters selected and test conditions applied were: temperature (23°C and 35°C), relative humidity (50% and 70%), lightning (dark or light), oxidant exposure (with and without ozone), mechanical wearing (according to ISO/FDIS 4918), using process (household products or sealant application), real ageing (indoor air office exposition).

These scenarios were applied to 5 selected floor coverings: resilient PVC floor covering, linoleum, wood laminate, raw exotic and pinewood parquets.

The testing protocol included two 28 days periods: from 0 to 28 days, emissions from the new materials were measured and from 29 to 56 days, the ageing process was simulated and emissions from the aged material were characterized.

Experiments were performed on new and aged building products using emission test chamber according to EN ISO 16000-9. Samples were collected 3 days after introduction of the building product in the chamber and all 7 days period between 7 to 56 days.

VOCs were sampled and analyzed according to ISO 16000-6 (2011). Samples were collected on Tenax TA sorbent tubes (Perkin Elmer) at 80 mL/min air flow rate and analyzed by thermal desorption (ATD Turbomatrix 350, Perkin Elmer) and gas chromatography (CG) with a flame ionization detector (FID) (Perkin Elmer Autosysteme XL) for quantification and a mass spectrometer (MS) (Perkin Elmer Turbomass) for identification and quantification. All VOCs emitted by the building products and detected at concentration above  $1 \mu g/m^3$  were identified. Carbonyl compounds (including formaldehyde, acetaldehyde) were sampled and analyzed according to ISO 16000-3 (2011). Samples were collected on DNPH coated cartridges (Waters) at 600 mL/min air flow rate and analyzed using HPLC-UV (Alliance, Waters) after liquid extraction with 5 mL of acetonitrile.

#### **3 RESULTS**

#### Influence of ageing on VOCs and carbonyls compounds emissions

VOCs and carbonyls compounds emissions identified during experiments conducted on new and aged floor covering materials were compared in order to analyse the influence of ageing process on emissions into indoor air. Modifications of emissions were observed during most experiments. For the wood laminate concentration of TVOC (total volatile organic compounds according to NF EN ISO 16000-9) was higher with relative humidity, using process, temperature and mechanical wearing scenarios. For the raw exotic parquet, an increase of formaldehyde concentrations was observed too, for temperature and oxidative exposition.

#### French mandatory labeling and AFSEET protocol compliance

Evaluation of emissions from the five tested floor coverings was realized according to the French mandatory labeling procedure (decree  $n^{\circ}$  2011-321) and to the AFSSET protocol (AFSSET, 2009) on new (i.e., after 28 days) and aged (i.e., after 56 days) test specimen. For the resilient PVC floor covering, the label was not modified with the different ageing scenario, while the other tested products showed different label for some specific ageing scenario. Table 1 presents results of experiments conducted on the wood laminate.

	new	Ageing scenario						
Parameters		relative humidity	lightening	using process	oxidation exposition	real ageing	temperature	mechanical wearing
French mandatory labeling	A+	A+	A+	A+	A+	A+	А	А
AFSSET compliance	Yes	Yes	Yes	Yes	Yes	Yes	No	No

#### Table 1. Evaluation of the wood laminate

#### **4 DISCUSSION**

For specific scenarios, in particular those involving oxidation and high relative humidity exposure of linoleum and raw pine wood parquet, significant modifications of VOCs emissions were observed compared to new products. Consequently, these experiments will be repeated and additional metrology will be implemented to study the potential formation of volatile gaseous and particulate by-products. A specific methodology to characterize oxygenated organic compounds in both gaseous and particulate phases (Rossignol et al., 2012) and c-TOF AMS (Compact Time-of-Flight Aerosol Mass Spectrometer) to evaluate the potential formation of secondary organic aerosol (SOA) will be used. These experiments are in progress.

#### **5 CONCLUSIONS**

The impact of wear conditions and use of building products on their middle and long-term indoor emissions was studied for 5 floor covering: resilient PVC floor covering, linoleum, wood laminate, raw exotic and pinewood parquets. Different scenarios were tested: high temperature, high relative humidity, lightning, oxidant exposure, mechanical wearing, using, and real ageing (indoor air office exposition). For specific scenarios, in particular those involving oxidation and high relative humidity exposure, significant modifications of VOCs emissions were observed compared to new products.

#### ACKNOWLEDGEMENT

The authors would like to thank the Agence de l'Environnement et de la Maîtrise de l'Energie (ADEME) for their financial support through the CEMMAT project (APR "CORTEA" 2012, grant agreement n°1204C0017). Authors would also like to thank Priscilla Thiry and Gwendal Loisel (CSTB) for their help and involvement in the experiments and chemical analyses.

#### **6 REFERENCES**

- AFSSET. 2009. Composés organiques volatils et environnement intérieur Procédure de qualification des émissions de composés volatils par les matériaux de construction et produits de décoration (<u>https://www.anses.fr/fr/system/files/AIR2004et0011Ra-2.pdf</u>).
- Decree n° 321-2011. Décret n° 2011-321 du 23 mars 2011 relatif à l'étiquetage des produits de construction ou de revêtement de mur ou de sol et des peintures et vernis sur leurs émissions de polluants volatils. *Journal Officiel de la République Française*. 23 mars 2011.
- Lee D.S. et al. 1996. The potential impact of ozone on materials in the U.K.. *Atmospheric Environment*. 30 (7), pp 1053-1065.
- Lee Y.K., Kim H.J. 2012. The effect of temperature on VOCs and carbonyl compounds emission from wooden flooring by thermal extractor test method. *Building and environment*, Vol. 53, pp 95–99.
- Reiss R. et al. 1995. Ozone reactive chemistry on indoor latex paint. *Environmental Science and Technology*. 29 (8), pp 1906–1912.
- Rossignol S. et al. 2012. Development of parallel sampling and analysis for the elucidation of gas/particle partitioning of oxygenated semi-volatile organics: a limonene ozonolysis study. *Atmospheric Measurment Technique*. 5, pp 1459-1489.
- Weschler C.J. et al. 1992. Indoor chemistry: ozone, volatile organic compounds, and carpets. *Environmental Science and Technology*. 26 (12), pp 2371-2377.