



**HAL**  
open science

## State of the art of particle emissions in thermal spraying and other high energy processes based on metal powders

G. Darut, Sébastien Dieu, Benoît Schnuriger, A. Vignes, Martin Morgeneyer, F. Lezzier, F. Devestel, A. Vion, C. Berguery, J. Roquette, et al.

### ► To cite this version:

G. Darut, Sébastien Dieu, Benoît Schnuriger, A. Vignes, Martin Morgeneyer, et al.. State of the art of particle emissions in thermal spraying and other high energy processes based on metal powders. Journal of Cleaner Production, 2021, 303, pp.126952. 10.1016/j.jclepro.2021.126952 . ineris-03217688v2

**HAL Id: ineris-03217688**

**<https://ineris.hal.science/ineris-03217688v2>**

Submitted on 24 Apr 2023

**HAL** is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.



Distributed under a Creative Commons Attribution - NonCommercial 4.0 International License

## ***State of the art of particle emissions in thermal spraying and other high energy processes based on metal powders***

**G. Darut\***

*UBFC, ICB-PMDM-LERMPS UMR6303, 90010 Belfort, France*

**S. Dieu, B. Schnuriger, A. Vignes**

*INERIS, 60550, Verneuil-en-Halatte, France*

**M. Morgeneyer**

*UTC, rue du Dr. Schweitzer, CS 60319, 60203 Compiègne, France*

**F. Lezzier**

*APS Coatings, rue de la Mare Blanche, 77186 Noisiel, France*

**F. Devestel**

*Phosphoris MP-Filter, 4, place Louis Armand, 75012 Paris, France*

**A. Vion**

*BV PROTO, Rue de Leupe, 90400 Sévenans, France*

**C. Berguery**

*TOYAL, route de Lescun, 64490 Accous, France*

**J. Roquette**

*Blue Industry and Science, 208 B rue La Fayette, 75010 Paris, France*

**O. Le Bihan**

*INERIS, 60550, Verneuil-en-Halatte, France*

\*The correspondence has to be address to:

Geoffrey Darut

ICB-PMDM-LERMPS

Université de Technologie de Belfort-Montbéliard

site de Sévenans

90010 Belfort cedex

France

Tél. +33 (0) 384 583 236

[geoffrey.darut@utbm.fr](mailto:geoffrey.darut@utbm.fr)

1 **8970 words**

2

### 3 **Abstract**

4 Thermal spray is a high energy-based process, like additive manufacturing and powder atomization, leading to fine  
5 particle emission. But there is little information about these nanoparticles and their characteristics: workers'  
6 exposure, filtration efficiency, dustiness. This paper aims to update the knowledge of the thermal spray community,  
7 to focus on thermal spraying and to a lesser degree on powder atomization and additive manufacturing technology,  
8 regarding emissions due to the high energy-based process. The three processes are presented before introducing an  
9 updated survey of thermal spray activities in France. The main thermal spray equipment is wire arc and plasma  
10 spraying. The main metal used is Al and Ni. The paper also highlights the lack of knowledge among workers on  
11 thermal spray emissions. Most workers are not made aware of collective protection (emission filtration equipment  
12 used) and personal protection (PPE). A complete bibliographical review is presented on the problem of ultrafine  
13 particle emissions mainly for the thermal spray process. Ultrafine particles are always characterized inside a working  
14 environment. The objective of this article is to list all publications related to ultrafine particle emissions around the  
15 working environment of a thermal spray process to raise awareness of the academic and industrial communities  
16 about the actual risks associated with this exposure. Finally, the authors are looking at the list of dust filtration  
17 equipment by presenting their advantages and disadvantages for particle filtration.

18

### 19 **Key words**

20 Thermal spray; emissions; nanoparticles; dust equipment; filtering; safety

21

### 22 **1. Introduction**

23 High temperature processes related to metal powders (e.g. atomization, thermal spraying, additive manufacturing)  
24 lead to the production and release of fines and nano-sized metal particles (Trompetter et al., 2016; Stefaniak et al.,  
25 2019). There is a lack of knowledge about the properties of these emissions and their management (collection,  
26 confinement or remediation), although the consequences of these ultrafine particles on health have been widely

27 demonstrated, in particular because of their inhalation without respiratory protection or collective aspiration  
28 (Reijnders et al., 2006).

29 The current French legislation requires reducing emissions into the environment in both gaseous and particulate  
30 form. This is particularly true for industries using powder metallurgy processes. Among the various existing  
31 processes, thermal spraying is probably the one with the most numerous configurations both in terms of energy  
32 sources (plasma, flame, electric arc) and materials used (metals, ceramics, polymers, composites, etc.). The principle  
33 of this technology is to combine a heat source with gases to melt a precursor material usually in the form of  
34 micrometric powder, and to accelerate the resulting molten particles towards a substrate.

35 Another powder metallurgy process which is currently on the rise is additive manufacturing, in particular selective  
36 laser melting of metal (so-called SLM technology). The energy source is a laser radiation applied to melt the powder.  
37 This process generates metal vapors. The operations are carried out in a closed chamber during the production phase.  
38 The common approach of these two powder metallurgy processes is to use of a powder as a raw material. In the case  
39 of metals, one method to make these powders from a liquid molten bath is atomization. Different methods can be  
40 used: blowing the surface of the molten bath with a jet of cold gas or blowing a stream of molten metal liquid with  
41 cold gas from surrounding nozzles, in order to generate droplets atomization that quickly solidify to form the  
42 powder.

43 Whichever process is used among the three presented, an exhaust management device allows to treat particles  
44 emitted to collect and/or treat them. However, there is relatively little information on the performance of this system,  
45 especially since the characteristics of these emissions are not well known. In addition, gas and particulate emissions  
46 do not only affect the core of the process, but the challenge is to consider the entire manufacturing chain, particularly  
47 the pre- and post-process stages. Environmental management allows good practice of emission control. Different  
48 issues are at stake, including organizational structure, practices, procedures and processes. The main objective is to  
49 provide companies with more information about environmental issues and emissions, for example decisions on the  
50 substitution of raw materials, decisions on the implementation of central or decentralized treatment or control for  
51 wastewater/waste gas, etc. (Brinkmann et al., 2016).

52 The general purpose of this paper is to update our knowledge about emissions due to thermal spraying particularly,  
53 and to a lesser degree to additive manufacturing and powder atomization processes. The authors will first detail the  
54 different processes. The results of a survey conducted about thermal spraying in France will then be presented

55 followed by a review of papers on thermal spray emissions. They will also discuss scientific results and survey data.  
56 Finally, the authors will present an overview of dust equipment for emission control.

57

## 58 **2. High energy processes based on metallic powders**

### 59 **2.1 Metallic powder manufacturing**

60 The metallic powder manufacturing currently benefits from the growth of additive manufacturing (Thomas, 2016;  
61 Tofail et al., 2018). The market is divided into two broad categories: plasma and gas atomization. For additive  
62 manufacturing or plasma spraying, the particle shape and size distribution are very important to optimize the use of  
63 the powder in the process and optimize the properties of the coatings or parts obtained. Powders resulting from  
64 plasma atomization perform better than other powder manufacturing processes (uniformity, spherical shape, very  
65 fluid). Gaseous atomization is the most popular technique used to produce metallic powders. The objective is to  
66 transfer kinetic energy from a high velocity gas stream expanded through a nozzle, to a filament of molten metal,  
67 resulting in disintegration into metal droplets. During this process, the material in the form of a metal bar is melted  
68 by induction in a crucible. Once the metal is completely liquid, the stopper bar used to prevent the liquid from  
69 transferring to the lower part of the process is removed to allow the molten metal to flow. The metal melt jet exits  
70 vertically by gravity from a hole/nozzle. The jet is surrounded by a gas flow from one or several jets which blow the  
71 liquid metal to generate a stream of droplets which solidify quickly to produce the powder (see Figure 1). The  
72 behavior of the metal liquid jet is important in determining the particle size distribution. Different atomization  
73 devices are available to generate metal powders.

74 The main global providers of metal powders using a plasma atomization process are located in Quebec: Tekna,  
75 AP&C and PyroGenesis Additive. Regarding gas atomization, a technique which is over 100 years old,  
76 manufacturers operate mainly in metallurgical industry: Carpenter and Praxair in the United States, VDM Metals in  
77 Europe and Sanyo Special Steel in Japan, for example. On the French territory, the main manufacturers are Toyal,  
78 Hermillon, Erasteel/Aubert & Duval, Tekna. Some research laboratories or technology platforms such as ICB-  
79 LERMPS, ONERA/MATMECA or Metaforsch aim to develop specific metal powders or alloys.

80

### 81 **2.2 Additive manufacturing**

82 Additive manufacturing can be described as the transformation of a 3D model into a 3D object, using a raw material  
83 and a heat source (Niaki et al., 2000). Additive manufacturing is a family of processes including selected techniques  
84 depending on the state (solid, liquid) and nature (plastic, polymer, metal, etc.) of the filler material (Dobrzanski,  
85 2017). First a virtual 3D CAD model is designed. This file is then converted to be understood by the additive  
86 manufacturing equipment (STL being the most commonly used). The software ‘slices’ the STL files into thin layers.  
87 Once the software has sent the instructions to the additive manufacturing equipment, the pattern is built layer upon  
88 layer (see Figure 2). The Selective Laser Melting (SLM) additive manufacturing process deposits a few ten  
89 micrometers thick bed on a support plate. The powder is melted locally with a laser spot based on the geometric  
90 parameters defined by the CAD file of the final part. The melted powder solidifies rapidly forming strings of solid  
91 material. At the end of this stage, the support plate goes down a little to allow the deposit of a new powder bed. This  
92 is repeated until completion of the finished product.

93 The additive manufacturing market is rapidly growing due to increasingly mature users and diversified uses (Debroy  
94 et al., 2019). Sales of equipment have seen an average annual growth of nearly 27% in recent years (Pipame, 2017).  
95 The R&D French sector includes 57 centers of excellence (Institut Carnot France, 2017) and 2,116 companies (BPI  
96 France, 2018). Aeronautics, space, medicine, luxury, mold/tool manufacturing, automotive are the main business  
97 sectors. In France, metallic materials are the most used with 40% of activities (Institut Carnot France, 2017). The  
98 metal additive manufacturing market is estimated at €60.6 million in France: 30% for powders, 40% for equipment,  
99 and 30% for the manufacture of parts (Observatoire de la métallurgie, 2019). The French market is expected to  
100 double between 2018 and 2025, notably through the expansion of part manufacturing, to reach €122M in 2025  
101 (Pipame, 2017).

102

### 103 **2.3 Thermal spraying**

104 Thermal spraying is a common surface technique used in many industries such as transport, energy, biomedicine,  
105 electronics, etc. (Vardelle et al., 2016; Abbas et al., 2019). This technology belongs to the family of dry surface  
106 treatments. The principle is to spray a powder on a support to modify its properties, using a thermal and kinetic  
107 source (see Figure 3). Materials in the form of powders are usually injected into a heat source where they are heated  
108 and accelerated before being deposited on a substrate to form a coating. Thermal spraying shows great flexibility due  
109 to the following characteristics (Vuoristo, 2014): wide range of processes and sprayed materials (pure metals, metal

110 alloys, hard metals, ceramics, polymers), attractive production rate, high deposit efficiency, versatility of processes  
111 and adaptability to the shape of the components. Selecting the type of gun/torch used involves looking at different  
112 thermal/kinetic properties (jet at higher or lower temperature, at higher or lower speed). This selection is decisive as  
113 it will determine the conversion of energy available in the jet for the treatment of injected materials. The thermal  
114 spray process is selected depending on the material to be used (which also depends on the coating application: anti-  
115 corrosion, anti-wear, reloading, reduction of friction, thermal or electrical insulation, etc.), the substrate nature, etc.  
116 (Fauchais et al., 2014). The different systems are Atmospheric Plasma Spraying (APS), High Velocity Oxy Fuel  
117 (HVOF), wire arc spraying, cold spray, etc. Among the various processes based on metallic powders and high  
118 energy, thermal spraying is undoubtedly characterized by the widest range of configurations of energy sources  
119 (plasma, flame, electric arc) and materials used. Thus, emissions are very diverse in terms of produced gases  
120 (ionization, recombination, combustion phenomena, etc.) and emitted particles (material, average size, reactivity,  
121 etc.) (Pawlowski, 2008). Moreover, the range of reactions complexity can vary. Thermal plasma is also used to  
122 manufacture nanoparticles (Samal, 2017).

123 A detailed survey of the INRS (French National Research and Safety Institute for the prevention of Occupational  
124 Accidents and Diseases) has mapped thermal spray facilities in France based on the processes and materials used,  
125 and the line of business (Savary, 2014). It shows that approximately 780 to 960 companies working in thermal  
126 spraying, with 75% of companies owning only one process in contrast with 2% of them working with five types of  
127 equipment. The main process was wire arc spray (more than 50% of companies). The APS process was five times  
128 fewer and the HVOF ten times fewer. This was consistent with the main material used, ZnAl (14%), followed by Ni  
129 base material (9%) and Al (8.5%). In France, thermal spray was mostly linked to small companies, using only one  
130 process.

131

### 132 **3. CaRPE survey**

133 To update the INRS work (Savary, 2014), a survey of French thermal spray companies was conducted in 2019. The  
134 questions were aiming at improving the understanding of their activities (processes, materials) regarding emission  
135 hazards (personal protective equipment) and capture systems (cleaning, filtration, measurements). The questions are  
136 listed in the Table 1, and the answers are presented in Figures 4 to 9.

137 Among around 100 companies, only 10 answered. As a result, the statistics presented barely give a qualitative trend  
138 for 2019. The key is to know the company working environment when it comes to thermal spray activities.  
139 Figure 4 shows that more than 80% of the French companies surveyed are equipped with wire arc spraying and APS  
140 processes. Then HVOF/HVAF reach 78%. These results are in line with the INRS wide survey (Savary, 2014). For  
141 APS and HVOF/HVAF, the base materials are Ni and Cr, as shown by the INRS survey (see Figure 5). For wire arc  
142 and flame spraying, Al, Cu and Fe base material are mostly used. In the INRS survey, Zn was predominant. These  
143 results indicate that small companies contacted for the survey probably did not answer due to lack of time or the  
144 primary purpose of the survey: emissions. Most of the time, companies are reluctant to discuss emissions and staff  
145 protection issues.  
146 The survey shows that the majority of thermal spray booths is inaccessible during operations and the main air capture  
147 is usually located at the emission source and on the booth wall (see Figure 6). Furthermore, 67% of companies do not  
148 have suction over the powder feeder to evacuate aerosol formation during powder pouring.  
149 Regarding the companies' dust exhaust system, the most popular one is filtration using a fibrous media, namely a  
150 cartridge (see Figure 7). It is interesting to highlight that 20% of companies do not really know which equipment is  
151 installed. Furthermore, the effectiveness of the media is unknown in most cases, and various classes of media are  
152 used (EPA, HEPA). This information shows companies' lack of interest in selecting a dust collector, because there is  
153 little information (scientific papers, studies) about the efficiency of dust collectors.  
154 Figure 8 presents the protective equipment worn by operators during thermal spray operations. In most cases, it  
155 includes face masks and FFP3 cartridges. But there are still some companies where operators do not wear respiratory  
156 PPE. Despite information in the literature regarding emissions and exposure, a company policy is paramount.  
157 Furthermore, the right equipment must be worn for each step where there is a risk of contact with powder/dust (booth  
158 cleaning, powder pouring, etc.). Moreover, the efficiency class of respiratory protective equipment filters is not FFP3  
159 equivalent for all. Booths are usually cleaned once a week. But the selected method to remove dust is still surprising.  
160 For example, 33% of operators use a broom and 22% use a compressed air-blower. Finally, Figure 9 confirms that  
161 66% of companies set aside the emission problem and do not plan emission measurements, such as sampling on a  
162 workstation or on the dust collector exit.

163

#### 164 **4. Emissions from processes**



165 Whatever the process (atomization, thermal spraying or additive manufacturing), using powder and a heat source  
166 leads to particle emissions. For thermal spraying, the range of materials is very large (almost all metals) with a  
167 powder size scaling from micrometers to sub-micrometers and nanometers, depending on the surrounding  
168 atmosphere around the process (air, neutral gas, vacuum). Emissions vary greatly based on these conditions.  
169 Moreover, the thermal spray deposition efficiency range is largely dependent on the process, 10 to 99.9% (Fauchais  
170 et al., 2014). A significant proportion of particles, residues and matter gets lost in the booth. The initial average size  
171 of the powder ranges from 5 to 150 micrometers. But after spraying, some matter is vaporized, sprayed out of the  
172 substrate, lost after rebounding at the surface. To date, the conversion rate of micrometric particles into ultrafine  
173 particles is not known. No study has investigated this question. In most cases, an aerosol is generated. For powder  
174 atomization, the process is based on aerosol manufacturing by the blowing of a liquid jet. Selective laser melting  
175 generates matter emissions when the laser spot melts the powder. Figure 10 illustrates these emissions around the  
176 thermal source.

177 The scientific community has been studying emissions from powder metallurgy processes for several years.  
178 Regarding metal powder atomization, the aim is to collect all particles generated by the process. Most of them enter  
179 the final container under the atomization tower. But some of them accumulate inside the tower leading to possible  
180 emissions during maintenance. As it is a closed-circuit process, emissions are channeled inside during the  
181 manufacturing phase. No study was found on the characterization of emissions during metal atomization.  
182 Selective laser melting with metals usually occurs inside a specific device in a closed loop. During metal processes,  
183 emissions are channeled inside the equipment, whereas for plastic and polymers, some equipment do not use any  
184 exhaust and filtration system. As a result, the operator is exposed to emissions of ultra-fine particles. On plastics,  
185 these emissions have been found in very high concentrations (Stephens et al., 2013; Azimi et al.). Regarding metal  
186 particles, Keller et al. (2018) and Bau et al. (2019) highlighted the high number of nanoparticles generated during the  
187 additive manufacturing process near the source inside the process:  $2.5 \cdot 10^6$  to  $4.5 \cdot 10^6$  #/cm<sup>3</sup>. Operators who handle  
188 metal powders run the risk to be exposed to particles (Graff et al., 2017; Mellin et al., 2016). Another study confirms  
189 the presence of nanoparticles (around 15 nm) around metal additive manufacturing equipment (Gomes et al., 2019).  
190 A review of Chen et al. confirms these results, showing that these emissions are very real and unintentional during  
191 the operator's handling (Chen et al., 2020). A methodology must be developed to avoid exposures, especially

192 regarding the management of this risk (Souza et al., 2019) and the design of the working environment of the process  
193 (Ljunggren et al., 2019).

194 For thermal spraying, the available studies essentially focus on describing thermal spray activities in terms of  
195 processes, materials and applications. Some scientific papers nevertheless look at characterizing emissions for a few  
196 combinations of materials, in most cases around the process. In France, the INRS has carried out studies in thermal  
197 spray activities (Mater and Savary, 2014). Their survey reveals that in 12% of French thermal spray companies,  
198 employees do not wear respiratory protective equipment (Savary, 2014), as confirmed by our CaRPE survey.

199 Moreover, even if there is a ventilation system in the booth, a significant number of employees enter without  
200 respiratory equipment (Savary, 2015). A study was carried out on the emissions of arc-wire spray processes that emit  
201 metal vapors (Grippari, 2012). The measurements showed numerous particles with an aerodynamic diameter less  
202 than 100 nm. The INRS also raises the alarm against the large quantity of ultrafine particles below 100 nm generated  
203 by the arc-wire spray process and recommends a number of technical measures to use filtration to treat the nature of  
204 effluents (Bémer et al., 2010). This same institute has also published some emission data on NiCr alloy and some  
205 elements of information on aluminum and zinc materials in various processes (first level information only). A study  
206 conducted by another French health institute measured levels 15 times higher than the occupational exposure limit  
207 value for CrVI for sprayed materials containing chromium or chromium oxides (CARSAT, 2013). Similarly,  
208 operators who thermally spray Cr using plasma are exposed to CrVI with concentrations above VLEP-8h of  $1 \mu\text{g}/\text{m}^3$   
209 (Jacoby et al. 2017). Levels of urinary excretion of Ni metal for exposed thermal spray operators, all processes  
210 combined, are relatively high compared to those unexposed. Viana et al. and Salmatodinis et al. show that high  
211 concentrations of ultrafine particle emission are measured during the APS process ( $3.7 \times 10^6/\text{cm}^3$ ), with a particle  
212 size distribution between 28 nm and 45 nm (Viana et al., 2017; Salmatodinis et al., 2018). These emissions of  
213 nanoparticles can transfer outside the spray enclosure where workers are not necessarily protected by PPE  
214 (Salmatodinis et al., 2020). With the HVOF process, the same trend is found with exposure concentration of dust  
215 particles reaching  $140 \text{ mg}/\text{m}^3$  (Huang et al., 2016). A study compared three spray processes for material residues  
216 (cobalt, chromium, and nickel) in the urine of operators (Chadwick et al., 1997). The plasma process is the most  
217 emissive. In Greece, a thermal spray company completed some measurements to control air quality (Petsas et al.,  
218 2007). It appears that concentrations of particles and heavy metals were predominant during the cleaning and  
219 maintenance phases of the spray booth. The INRS survey indicates that 23% of operators use a broom or a blow gun

220 to clean work areas (Savary, 2015). The Thermal Spray Society (2013) publishes documents on risks surrounding the  
221 process and recommended protections. However, these documents only give an overview of the issues encountered  
222 and do not provide a clear answer on how to ensure health and safety in the workplace.

223 The scientific literature demonstrates the unintentional manufacturing of nanoparticles during thermal spraying. As  
224 the deposition efficiency is mostly around 50-60%, a part of the initial feedstock loss is transformed into ultrafine  
225 particles under the heat source. Some of these particles are sucked by the extraction system, but nanoparticles can  
226 deposit around different parts in the booth (robot, coated piece, booth corners, etc.). So, at the end of spraying, the  
227 operator is always exposed to nanoparticles through his actions in the booth (object displacement, walking on the  
228 ground, air flow due to his movements, etc.). The release due to the induced air motion can play a role in the  
229 exposure. The CaRPE survey demonstrates that wearing protective equipment is not ubiquitous and not all  
230 companies are aware of the risks of exposure to ultrafine particles. Operators wear protections without any  
231 knowledge regarding the risks and consequences of not wearing any. This is even more damaging because the two  
232 most used materials are Cr and Zn. Several analyses show that Cr can be found in urinary samples, and CrVI can be  
233 formed during spraying via different processes. Zn material mainly used with wire arc spray process under  
234 atmospheric conditions can generate ZnO oxide at the nanometer scale which could induce a health hazard  
235 (Subramanian et al., 2018). To make matters worse, according to the INRS and CaRPE surveys, booth cleaning is  
236 often carried out with a broom or a compressed-air blower only to induce the resuspension of ultrafine particles in  
237 the air. Normally, nanoparticles are quickly sucked by the air extraction systems, limiting the operator's exposure.  
238 But as shown by Bemer et al. (2010) (2013b), the most widely used dust collector with a cartridge fibrous media is  
239 rapidly clogged up with nanoparticles. The difficulty to clean cartridges, even by gas pulse, can explain the pressure  
240 drop inside the exhaust pipe of the booth. As a result, dust particles from the thermal spray remain at high levels in  
241 the booth, increasing the operator's exposure after the coating manufacturing.

242

## 243 **5. Dust equipment for emission control**

244 Thermal spraying induces gaseous emissions that contain particles of various average sizes, morphologies,  
245 compositions. Around the process, the waste gas generated can be divided into ducted and diffuse emissions. The  
246 first type can be cleaned whereas the second one can only be prevented. Industrial emissions can usually be classified  
247 as shown in Table 2 (Brinkmann et al., 2016).

248 Waste gas treatment devices aim at processing different chemical elements such as gas, particles, vapors of volatile  
249 liquid substances, gaseous air contaminants. The system is linked to a unique emission source as the treatment unit is  
250 exclusively designed for a specific waste gas composition. Most processes show material melting through their heat  
251 source at relatively high temperatures. The raw material is a powder in a melting state, upstream (thermal spraying,  
252 additive manufacturing) or downstream (powder atomization) of the process. The induced emissions consist of a  
253 variety of gases and particles (composition, particle size, concentration, etc.).

254 An aerosol is defined as a set of solid or liquid particles in suspension (maximum limit speed of fall  $<0.25$  m/s) in a  
255 gaseous medium (Kulkarni et al., 2011). This term includes both fumes, dusts and mists, but not vapors. Fumes are  
256 defined as dispersions of very fine solid particles resulting sometimes from condensation or incomplete combustion.  
257 Dust is defined as any suspended solid particles. A particle is defined as a small part of solid or liquid material  
258 suspended in the air or likely to be. Within an emission, particles are mainly distinguished by their size (see  
259 Figure 11):

- 260 • PM10 particles: aerodynamic diameter less than  $10\ \mu\text{m}$ ;
- 261 • PM2.5 aerodynamic diameter less than  $2.5\ \mu\text{m}$ ;
- 262 • PM1 aerodynamic diameter less than  $1\ \mu\text{m}$ .

263 This classification was created based on inhalation hazards level. Particle characteristics are linked to the deposit  
264 area in the pulmonary system. The fraction of inhaled particles depends on their aerodynamic diameter (diameter of a  
265 sphere with the density of  $10^3\ \text{kg/m}^3$  and a falling rate in calm air environment which is equal to that of the particle in  
266 the same conditions) and on the type of breathing (nose, mouth). The pulmonary area will depend on the inhalable  
267 fraction of well-defined sub-fractions: thoracic and alveolar. Regarding the three processes based on metallic  
268 powders and high energy (thermal spraying, powder atomization, additive manufacturing), the main components of  
269 emissions are solid particles. So, the waste gas treatment device will depend on the particle characteristics.

270  
271 A dust collector is designed to collect the dust containing particles and separate these particles from the gas . The  
272 choice of process starts with an efficient characterization of the fumes to be treated, including:

- 273 • solid or liquid particles,
- 274 • temperature, because it will alter the density, the viscosity, the humidity, the conductivity of particles and  
275 affect the selection of the material for filters, for example;

- 276 • granulometry;
- 277 • concentration at the capture inlet and at the outlet;
- 278 • vector fluid;
- 279 • fluctuating, pulsed or continuous gas flow;
- 280 • neutral, corrosive or flammable medium;
- 281 • pressure.

282 Dust collectors can be wet (removal of dust from the air by water filtration) or dry (removal of dust from the air  
283 through filter media or electrostatic forces). The collected air is filtered by dust extractors. In order to capture the  
284 dust, different attraction methods are available: gravity, molecular (cohesion and adhesion forces) and electrical (or  
285 repulsion).

286 Therefore, different types of equipment were designed to filter or sort this dust, among which 5 main techniques  
287 (Siret, 2001):

- 288 • settling chambers;
- 289 • centrifugal separators or cyclones;
- 290 • electrostatic precipitators;
- 291 • filtration by fibrous media;
- 292 • wet dust collectors.

293

### 294 **5.1 Dry collectors**

295 Settling chambers consist of an empty chamber where the fumes/waste gases circulate with a low speed. This leaves  
296 time for gravity to separate particles from gas (>10-50 µm). To improve the deposition efficiency of particles, it is  
297 necessary to:

- 298 • adjust the chamber design with baffles or lamellae to reduce gas velocity;
- 299 • increase the active force of particles by centrifugal force (baffled precipitator, centrifugal separator) or  
300 electric force (electrostatic precipitators);
- 301 • capture particles in liquid droplets (hydraulic dust collectors, wet electrostatic precipitators);
- 302 • agglomerate particles by electrical or sonic agglomeration.

303 Settling chambers are often used as a first device in filter systems to remove large particles.

304

305 In a centrifugal separator, fumes will be rotated to use inertia to collect particles. Centrifugal force moves the dust  
306 towards the wall to be collected (cyclone effect) thanks to a double vortex. Cyclones are sedimentation chambers  
307 where the effect of gravity is increased by centrifugal force. The largest particles are removed. Performances are set  
308 by the geometry of the system (height, diameter, tangential velocity). Efficiency increases with high airspeeds in a  
309 small diameter and long cylinder. This is the cheapest and most robust equipment with a very wide operating  
310 amplitude (temperature, pressure). However, performance is limited to particle sizes greater than 10 microns. The  
311 efficiency is 95% for particles > 15 µm. The smallest ones should be separated with another device. Wet cyclones aim  
312 to increase efficiency when separating fine particles.

313 There are two main types of cyclones:

- 314 • reverse flow cyclone (lateral inlet);
- 315 • straight-through cyclone (axial inlet);

316 Other less used types are: electro cyclones with an electrode that charges particles to hit the walls, multi-cyclones.

317

318 Electrostatic precipitators (ESP) use an electric force applied to the charged particles by ionization of the fumes. A  
319 wire placed in a tube or pulled between two plates is brought up to a highly negative voltage creating a corona  
320 discharge. The gases that make up the smoke are then excited, tearing out electrons that, by collision, create ions and  
321 radicals that will charge particles. They are then subjected to an electric field to be attracted to a counter electrode  
322 where they will pile up and form a deposit. There are different separators: dry wire plate or pipe ESP, wet wire plate  
323 or pipe ESP. However, this equipment has been listed as a possible explosion risk due to its technical configuration  
324 and its electrostatic property which can be a source of ignition (Chhabra, R. et al., 2019). ESPs are not recommended  
325 for materials with explosive properties (Peukert et al., 2001). The authors believe that ESP would be suitable to  
326 remove ultrafine oxidized dust. In the case of metal dust, a pre-combustion step would be required to avoid the  
327 formation of an explosive atmosphere in the ESP. Ultrafine metal dust is likely to react with water to produce  
328 hydrogen (e.g. aluminum dust) and in that case, neither dry ESPs nor humid ESDs can be used exposed to air. If the  
329 risk analysis shows that such a system could be used (e.g. passivated powders, mixture with inert solid particles, low  
330 flow rate associated with a sufficient ventilation rate), it is likely that an explosion mitigation system should be  
331 implemented such as an explosion vent.

332

333 The dust collector by fibrous media (fabric filter) consists of a main box (filter elements, high-pressure air pulse  
334 cleaning system, hopper collecting dust). Polluted air enters at the bottom of the dust collector to come out above  
335 after passing through the filters. Unlike with cyclones where disposal is continuous, with fibrous media collectors,  
336 particles accumulate on the outer surface of the filter media and form a deposit that will induce a pressure drop  
337 during the operation of the dust collector. These filters are cleaned to limit the pressure drop caused by clogging  
338 fibers, fabrics or other felts. There are different cleaning methods:

- 339 • shaking, where the filter is gently shaken in all directions on a mechanical device;
- 340 • counterflow gas, where the suction is stopped and air is blown through the filters in the opposite direction to  
341 that of the filtration;
- 342 • gas pulse, where a pulse of medium air pressure is propelled inside the sleeve, generating a wave of pressure  
343 and deformation that will allow the dust cake to come off. This type of unclogging is possible without the  
344 need to isolate the whole box, and sleeves nearby can continue to operate. The benefits of this method are  
345 its high efficiency and the possible use of non-compartmentalized filters. In contrast, the sleeves are more  
346 stressed and wear faster.

347 These actions remove the cake made of particles which is collected in a hopper. Unclogging is performed at regular  
348 intervals depending on the pressure drop. The first unclogging operations make it possible to find pressure drop  
349 values close to those of a new fibrous media, for the first cycles. Once deposited on the fibrous media, particles  
350 remain either on the surface or inside the media. This phenomenon increases during the process. After a while, the  
351 filter elements become irremediably clogged and must be replaced. The presence of ultra-fine particles accelerates  
352 the clogging phenomenon. The media is less efficient due to the strong adhesion of particles. To delay the clogging,  
353 it is advisable to reduce the filtration speeds by increasing the filtration area, or to add a coarser filter (prefilter for  
354 large particles). There are three filter media technologies:

- 355 • fibrous media;
- 356 • consolidated porous media, such as sintered ceramics but generating high-pressure losses;
- 357 • unconsolidated granular porous media, such as sand columns but showing low efficiency against fine  
358 particles.

359 When filtering an aerosol, a particle is screened by a fibrous filter (particle size larger than the pore size). In the  
360 absence of external force fields such as a magnetic field, particles are captured via gravity through a fiber filter in 3  
361 steps:

- 362 • inertia: particles cannot follow the current line during fiber crossing and collapse against it (diameter greater  
363 than 1  $\mu\text{m}$ );
- 364 • direct interception when particles follow the current line but approach the fiber at a distance shorter than  
365 their radius (greater than 100 nm);
- 366 • Brownian scattering for particles smaller than 100 nm, where their trajectory passes close enough to the  
367 fiber to undergo a deflection under the influence of the Brownian motion.

368 Electrostatic forces can also be added with a metal media before calculating the filter efficiency. Between 100 nm  
369 and 500 nm, a minimal degree of operational efficiency is reached because the three capture mechanisms are not  
370 preponderant. Some particles are too large to be affected by the diffusion phenomenon and too small to be  
371 intercepted or impacted. These are the most penetrating particles (MPPS: Most Penetrating Particle Size). It is in this  
372 area that the efficiency of high efficiency particles (HEPA) and ultra-low penetration (ULPA) air filters is calculated.  
373 The fiber filters consist of natural, metallic, or synthetic fibers. Generally, fibers consist of fiberglass, polyester or  
374 cellulose. They are defined by different factors:

- 375 • compactness: volume of the fibers/volume of the filter;
- 376 • basis weight: filter mass/filter area;
- 377 • thickness;
- 378 • size distribution of the fibers;
- 379 • nature of the fibrous filters: fibrous woven, felt or nonwoven.

380 These fibrous filters can be mounted on different filtration systems: bag filters, cartridge filters. They can operate  
381 alternatively or continuously (it is possible to isolate the filter to be unclogged without stopping the ventilation).

382 Each of these filters exists in various ranges of efficiency depending on the industrial field and the fumes particles  
383 characteristics: very high efficiency (nuclear, clean room), high efficiency (indoor air, air conditioning), average  
384 efficiency (industrial effluents). For a medium and high efficiency, the deposition of particles (cake) on the surface  
385 of the media is eliminated mechanically whereas for very high efficiency, particles are captured inside and therefore  
386 filters must be changed.



387 An absolute filter is composed of a high-density pleated media made of fiber glass. Particles from the waste gas are  
388 collected. The design is often a cylindrical cell, and a pre-filter is necessary to remove the biggest particles. The  
389 absolute part is set for ultra-fine particles and nanomaterials.

390 The Carpe survey shows that the most popular filter is the cartridge filter (see Figure 7). But 20% of companies are  
391 unaware of their filter characteristics. In the thermal spray community, fibrous media filters are the most adapted to  
392 filter emitted particles. However, difficulties related to the regeneration of filters clogged by metallic nanoparticles  
393 are still relevant today. The rapid increase of the pressure drop with ineffective unclogging is still being investigated  
394 to control this issue (Khirouni et al., 2020a). To date, it means a frequent replacement of filter media.

395

## 396 **5.2 Wet collectors**

397 A wet collector, often named wet dust scrubbing, uses a liquid to intercept particles contained in the fumes. This  
398 device is widely used for its efficiency in reducing particulate emissions and especially soluble compounds such as  
399 acid gases and heavy metals. Wet collectors are often associated with other technologies, especially electrostatic  
400 precipitators. There are two mechanisms for dust capture: by impaction on a wet wall (packed column) or by  
401 collision with a dispersion of liquid droplets injected into a gas (venturi, spray column). The most common principle  
402 is impaction by inertia.

403 There are therefore several types of wet separators (Siret, 2001):

- 404 • spray towers: the spray occurs from top to bottom. They are widely used but not for dusting due to their low  
405 efficiency. The stripping mattress is composed of a mesh of fine ordered or disordered fibers, which capture  
406 particles. The efficiency is very good up to 1  $\mu\text{m}$ ;
- 407 • cross-current: the spraying is perpendicular to the flow of smoke. They are suitable for dust (99% efficiency  
408 for particles > 2  $\mu\text{m}$ ) but have a fairly high energy consumption (pump);
- 409 • foam: fumes cross a liquid layer supplemented with a surfactant. The phenomenon of diffusion explains an  
410 efficiency rate of 90% for 500 nm particles. There are a few pressure losses, but the cost is quite high;
- 411 • venturi type: this type is especially designed for dust while the previous ones basically focus on the  
412 purification of gaseous compounds. Gases are accelerated, which facilitates the interaction between the  
413 aerosol and the liquid regardless of the significant pressure loss. The efficiency rate is 99% for a dimension  
414 of 1  $\mu\text{m}$  but the energy consumption is important;

- 415 • bubble columns: the transported dust meets liquid bubbles and mixes with them, establishing a transfer from  
416 one phase to another;
- 417 • fibrous packing, moving-bed, plate, etc.

418 Tables 3 and 4 show the main characteristics of the different filters (abatement efficiency, benefits and limitations).  
419

## 420 **6. Thermal spray and emissions control efficiency**

421 Thermal spraying combines micrometric powder and high energy sources (flame, plasma, electric arc). The  
422 formation of the coating from the precursor generates nanoparticles that can be found in the spray booth or in the  
423 environment close to the cabin. The exposure of operators is then obvious and protective equipment has to be worn  
424 (Heriaud-Kraemer et al., 2003). In most cases, the nanoparticles are the result of the process as the initial feedstock is  
425 micrometer sized, even if nanoparticles (ceramics) can be used (Toma et al., 2008). Moreover, the solution precursor  
426 plasma spray process uses only salt solution feedstocks to manufacture coatings with physical and chemical reactions  
427 inside the heat source (Bertolissi et al., 2012). The use of plasma spraying under very low pressure allows vaporizing  
428 the initial powder creating nanoparticles and nanostructures (Fan et al., 2019; Darut et al., 2019). So, the resulting  
429 fine dust generated by the process must be captured by the exhaust system which has to be selected or configured  
430 based on the thermal spray dust properties. This way, an efficient ventilation flow inside the booth facilitates the  
431 capture of nanoparticles in the filtration system. The air velocity impacts directly on the dust drive to suction panels.  
432 It is linked to power characteristics of the exhaust filtration system and to pressure losses in the pipes and filter  
433 media. If the velocity is too low, dust accumulates on the booth floor or walls. That is why cartridge media (major  
434 filter system in thermal spray activity (Bemer et al., 2013b) as confirmed by the CaRPE survey) are cleaned by  
435 compressed air jet to prevent pressure loss and allow good ventilation. But with some processes, in particular wire  
436 arc spraying, filtration cartridges are often clogged. Bemer et al. underline the irreversible character of clogging due  
437 to the nature of the dust collected (Bemer et al., 2013a). Even with the use of a counter-current pulse-jet, cleaning  
438 seems to be inefficient. Granular beds, based on Brownian diffusion mechanism to capture ultrafine particles, could  
439 be a good alternative to conventional cartridge filters but no industrial pilot has yet been tested (Bemer et al, 2015a;  
440 Bemer et al., 2015b). A recent work of the INRS shows the possibility to improve cartridge cleaning using a pre-  
441 deposit (micrometer particles) on the surface of the filter media in order to improve the removal of ultrafine particles  
442 that would be deposited on the surface (Khirouni et al., 2020b). A different approach was proposed by Cho et al.:

443 spraying compressed air directly on the external surface of the filter rather than injecting pulse-jet air on its internal  
444 surface (Cho et al., 2020). This so-called air-washing cleaning method allows successful cleaning and regenerate the  
445 fibrous media, but also to reduce particle emissions. Some modeling has been developed to study the concentration  
446 of released nanoparticles during a thermal spray process (Ribalta et al., 2016). The measurements confirm the results  
447 of previous studies. When the thermal spray process occurs in a booth, a negative pressure is applied to confine dust  
448 inside. A problem can occur: the filtering system does not collect nanoparticles efficiently. The negative pressure can  
449 reintroduce the polluted air in the booth, according to the positioning of the exhaust system outlet in relation to the  
450 air compensation entry. In any case, nanoparticles will be rejected into the environment if the exhaust system is not  
451 appropriate.

452

## 453 **7. Conclusions**

454 Nanoparticles emission is crucial for processes based on metal powders and high energy such as thermal spraying,  
455 powder atomization and additive manufacturing. During processes, particles are in a liquid/vapor state in the thermal  
456 source. Generated nanoparticles are incidental. As a result, companies and operators must be aware of the risk and  
457 release into the environment. The different surveys on thermal spray activity demonstrate the lack of information and  
458 communication between the industry and scientific community. Various published papers state the health risk for  
459 unprotected operators around the process. A significant number of operators work without a protection adapted to  
460 thermal spray activity. It would therefore be necessary to characterize these emissions, and to make operators aware  
461 of monitoring and reduction. Different filtration devices can be used to treat thermal spray effluents and therefore  
462 adapted to the ultrafine particles generated. However, the use of fibrous media (filter cartridge essentially) is the  
463 most appropriate to retain this waste. The clogging issue of these media and therefore the suction flow pressure drop  
464 in the spray enclosure are still relevant. The risk is an increase of particles in the working booth and their presence at  
465 the end of the spraying, in contact with the operator.

466 The main recommendations for the thermal spray activity as well as the risks that may be encountered will be studied  
467 in a second part of this project. Various sampling operations and emission analyses of plasma spraying equipment  
468 will be carried out. Different areas will be targeted, such as at the level of emissions channeled upstream and  
469 downstream of the filtration system, at the workstation level as well as fugitive emissions. Various measurements

470 will be carried out: real-time particle size distribution, mass concentration of total suspended dust, heavy metals,  
471 sampling characterization by EDX/MET, etc.

472

## 473 **Acknowledgments**

474 The authors gratefully acknowledge financial support from French agency ADEME (Agency for ecological  
475 transition) as part of the CORTEA call of projects for the CaRPE project. They thank the French Ministry of  
476 Environment supporting INERIS through the P190 program.

477

478

## 479 **References**

480 Abbas, S. M., Elayaperumal, A., Experimental investigation on the effect of ceramic coating on engine performance  
481 and emission characteristics for cleaner production, 2019. *J. Clean. Prod.* 214, 506-513.

482 <https://doi.org/10.1016/j.jclepro.2018.12.040>

483 Azimi P., Zhao D., Pouzet C., Crain N. E., Stephens B., 2016. Emissions of ultrafine particles and volatile organic  
484 compounds from commercially available desktop three-dimensional printers with multiple filaments. *Environ.*  
485 *Sci. Technol.* 50, 1260–1268. <https://doi.org/10.1021/acs.est.5b04983>

486 Bau S., Rousset D., Payet R., Keller F.X., 2019. Characterizing particle emissions from a direct energy deposition  
487 additive manufacturing process and associated occupational exposure to airborne particles. *J. Occupational*  
488 *and Environmental Hygiene.* 17, 59-72. <https://doi.org/10.1080/15459624.2019.1696969>

489 Bémer D., Régnier R., Subra I., Sutter B., Lecler M. T., Morele Y., 2010. Ultrafine Particles Emitted by Flame and  
490 Electric Arc Guns for Thermal Spraying of Metals. *Ann. Occup. Hyg.* 54, 607-614.

491 <https://doi.org/10.1093/annhyg/meq052>

492 Bemer D., Subra I., Morele Y., Charvet A., Thomas D., 2013b. Experimental study of granular bed filtration of  
493 ultrafine particles emitted by a thermal spraying process. *J. Aerosol Sci.* 63, 25-37.

494 <https://doi.org/10.1016/j.jaerosci.2013.04.005>

495 Bemer D., Régnier R., Morele Y., Gripari F., Appert-collin J.-C., Thomas D., 2013a. Study of clogging and  
496 cleaning cycles of a pleated cartridge filter used in a thermal spraying process to filter ultrafine particles.

497 *Powder Technol.* 234, 1-6. <https://doi.org/10.1016/j.powtec.2012.09.035>

498 Bemer D., Morele Y., Regnier R., 2015a. Filtration of ultrafine metallic particles in industry. *Envir. Technol.* 36,  
499 2374-2380. <https://doi.org/10.1080/09593330.2015.1028471>

500 Bemer D., Wingert L., Morele Y., Subra I., 2015b. Feasibility of granular bed filtration of an aerosol of ultrafine  
501 metallic particles including a pressure drop regeneration system. *J. Air Waste Management Association.* 65,  
502 1119–1126. <https://doi.org/10.1080/10962247.2015.1064490>

503 Bertolissi G., Chazelas C., Bolelli G., Lusvarghi L., Vardelle M., Vardelle A., 2012. Engineering the microstructure  
504 of solution precursor plasma-sprayed coatings. *J. Therm. Spray Technol.* 21, 1148-1162.  
505 <https://doi.org/10.1007/s11666-012-9789-3>

506 BPI France, 2018. Les startups du marché de la fabrication additive et l'impression 3D (in French).  
507 <https://blog.lehub.bpifrance.fr/les-startups-du-marche-de-la-fabrication-additive-et-limpression-3d/> (accessed  
508 27 august 2020)

509 Brinkmann T., Santonja G. G., Yükseler H., Roudier S., Delgado Sancho L., 2016. Best Available Techniques  
510 (BAT) Reference Document for Common Waste Water and Waste Gas Treatment/Management Systems in  
511 the Chemical Sector, EUR 28112 EN, Pub. Luxembourg: Publications Office of the European Union,  
512 Luxembourg. <https://doi.org/10.2791/37535>

513 CARSAT, 2013. Le chrome VI en milieu de travail (in french), CARSAT (Nantes, 2013).  
514 [https://www.smtaquitaine.fr/uploads/media\\_items/chrome-vi-en-milieu-de-travail.original.pdf](https://www.smtaquitaine.fr/uploads/media_items/chrome-vi-en-milieu-de-travail.original.pdf) (accessed 27  
515 august 2020)

516 Chadwick J. K., Wilson H. K., White M. A., 1997. An investigation of occupational metal exposure in thermal  
517 spraying processes. *Sci Total Environ.* 9, 115-124. [https://doi.org/10.1016/S0048-9697\(97\)05487-9](https://doi.org/10.1016/S0048-9697(97)05487-9)

518 Chen R., Yin H., Cole I. S., Shen S., Zhou X., Wang Y., Tang S., 2020. Exposure, assessment and health hazards of  
519 particulate matter in metal additive manufacturing: A review. *Chemosphere* 259, 127452.  
520 <https://doi.org/10.1016/j.chemosphere.2020.127452>

521 Chhabra, R., Basavaraj, Madivala G., 2019. Chapter 14 - Health and Explosion Hazards. Coulson and Richardson's  
522 Chemical Engineering (Sixth Edition), Pub. Butterworth-Heinemann, 739-764. [https://doi.org/10.1016/B978-  
523 0-08-101098-3.00015-9](https://doi.org/10.1016/B978-0-08-101098-3.00015-9)

524 Cho H., Youn J. S., Oh I., Jung Y. W., Jeon K. J., 2020, A new air-washing method to clean fabric filters clogged  
525 with submicron fume particles: A pilot-scale study. *J. Hazard. Mater.* 383, 121186.  
526 <https://doi.org/10.1016/j.jhazmat.2019.121186>

527 Darut G., Niederhauser A., Jaccoud B., Sigrist M., Mock E., Planche M.-P., Liao H., Montavon G., 2019. VLPPS: an  
528 emerging process to create well-defined components by additive manufacturing. *J. Therm. Spray Technol.* 28,  
529 255-264. <https://doi.org/10.1007/s11666-018-0792-1>

530 DebRoy T., Mukherjee T., Milewski J. O., Elmer J. W., Ribic B., Blecher J. J., Zhang W., 2019. Scientific,  
531 technological and economic issues in metal printing and their solutions, *Nature Mater.*  
532 <https://doi.org/10.1038/s41563-019-0408-2>

533 Dobrzanski L. A., 2017. *Powder Metallurgy - Fundamentals and Case Studies*, Pub. IntechOpen, London.,  
534 <https://doi.org/10.5772/61469>

535 Fan X., Darut G., Planche M.-P., Feng X., Liao H., Montavon G., 2019. Characterizations of composite titanium  
536 nitride coatings deposited by very low-pressure plasma spraying. *J. Therm. Spray Technol.* 28, 265-272.  
537 <https://doi.org/10.1007/s11666-018-0777-0>

538 Fauchais P., Heberlein J. V. R., Boulos M., 2014. *Thermal Spray fundamentals – From powder to part*, Pub.  
539 Springer, London. <https://doi.org/10.1007/978-0-387-68991-3>

540 Gomes J. F., Miranda R. M., Oliveira J. P., Esteves H. M., Albuquerque P. C., 2019. Evaluation of the amount of  
541 nanoparticles emitted in LASER additive manufacture/welding. *Inhalation Toxicology.* 31, 125-130.  
542 <https://doi.org/10.1080/08958378.2019.1621965>

543 Graff P., Ståhlbom B., Nordenberg E., Graichen A., Johansson P., Karlsson H., 2017. Evaluating measuring  
544 techniques for occupational exposure during additive manufacturing of metals. *J. Indus. Ecology.* 21, 120-  
545 129. <https://doi.org/10.1111/jiec.12498>

546 Gripari F., 2012. *Caractérisation et filtration des aérosols nanostructurés : application aux fumées de projection*  
547 *thermique des métaux (in french)*, thesis, Université de Lorraine. [https://hal.univ-lorraine.fr/tel-](https://hal.univ-lorraine.fr/tel-01749361/document)  
548 [01749361/document](https://hal.univ-lorraine.fr/tel-01749361/document) (accessed 27 august 2020)

549 Hallé S., Nadeau S., Fatisson J., 2015. Engineered containment and control of airborne nanoparticles current statuts.  
550 *Int. J. of Safety and Security Eng.* 5(4), 336–351 <https://www.witpress.com/elibrary/sse-volumes/5/4/1050>

551 Heriaud-Kraemer H., Montavon G., Coddet C., Hertert S., Robin H., 2003. Harmful risks for workers in thermal  
552 spraying: A review completed by a survey in a French company. *J. Therm. Spray Technol.* 12, 542-554.  
553 <https://doi.org/10.1361/105996303772082297>

554 Huang H., Li H., Li X., 2016. Physicochemical characteristics of dust particles in HVOF spraying and occupational  
555 hazards: case study in a chinese company. *J. Therm. Spray Technol.* 25, 971-981.  
556 <https://doi.org/10.1007/s11666-016-0422-8>

557 Institut Carnot France, 2017. Cartographie des acteurs clés de la R&D en fabrication additive (in french).  
558 [https://www.instituts-carnot.eu/sites/default/files/images/CartoFabAdd\\_CETIM-filiere-Manufacturing-](https://www.instituts-carnot.eu/sites/default/files/images/CartoFabAdd_CETIM-filiere-Manufacturing-juil2017.pdf)  
559 [juil2017.pdf](https://www.instituts-carnot.eu/sites/default/files/images/CartoFabAdd_CETIM-filiere-Manufacturing-juil2017.pdf), (accessed 27 august 2020)

560 Jacoby N., Robert A., Antoine G., Biette P., Jeandel F., Lambert Xolin A. M., Melczer M., Remy A., Matera V.,  
561 Rousset D., 2017. Occupational exposure to chromium and nickel in thermal spraying workers: Preliminary  
562 biological and atmospheric assessments, 10th International Symposium on Biological Monitoring in  
563 Occupational and Environmental Health (ISBM-10), 1-4 october 2017 (Naples, Italy)

564 Keller F. X., Bau S., Payet R., Rousset D., 2018. Additive metal manufacturing emission characterization.  
565 *Proceedings of Roomvent & Ventilation 2018, Espoo (Finland), 2-5 june 2018.* ISBN 978-952-5236-48-4

566 Khirouni N., Charvet A., Thomas D., Bemer D. 2020a. Performances des médias pour la filtration des nanoparticules  
567 métalliques (in french). CFA 2020 - 33ème Congrès Français sur les Aérosols, Paris (France), 28-29 january  
568 2020. 10.25576/ASFERA-CFA2020-19677

569 Khirouni N., Charvet A., Drisket C., Ginestet A., Thomas D., Bemer D. 2020b. Precoating for improving the  
570 cleaning of filter media clogged with metallic nanoparticles. *Process. Saf. Environ.* 147, 311-319.  
571 <https://doi.org/10.1016/j.psep.2020.09.045>

572 Kulkarni P., Baron P. A., Willeke K., 2011. *Aerosol Measurement: Principles, Techniques, and Applications.* Ed.  
573 John Wiley & Sons, Hoboken. ISBN:978-1-118-00167-7

574 Ljunggren S. A., Karlsson H., Ståhlbom B., Krapf B., Fornander L., Karlsson L., Bergström B., Nordenberg E.,  
575 Ervik T. K., Graff P., 2019. Biomonitoring of Metal Exposure During Additive Manufacturing (3D Printing).  
576 *Safety Health Work* 10, 518-526. <https://doi.org/10.1016/j.shaw.2019.07.006>

577 Mater G., Savary B., 2014. Projection thermique : état des lieux en 2012, Hygiène et sécurité du travail (in french).  
578 INRS NT18. Pub. INRS, Paris. <http://www.inrs.fr/media.html?refINRS=NT%2018> (accessed 27 august 2020)

579 Mellin P., Jönsson C., Åkermo M., Fernberg P., Nordenberg E., Brodin, H., Strondl A., 2016, Nano-sized by-  
580 products from metal 3D printing, composite manufacturing and fabric production, *J. Clean. Prod.* 139, 1224-  
581 1233. <https://doi.org/10.1016/j.jclepro.2016.08.141>

582 Niaki M. K., Nonino F., 2000. *The Management of Additive Manufacturing*, Ed. Springer, London.  
583 <https://doi.org/10.1007/978-3-319-56309-1>

584 Observatoire de la métallurgie, 2019. *Fabrication additive métallique – Marché et métiers*. [https://www.observatoire-](https://www.observatoire-metallurgie.fr/sites/default/files/documents/2019-04/synthese-etude-fabrication-additive-metallique-2019_1.pdf)  
585 [metallurgie.fr/sites/default/files/documents/2019-04/synthese-etude-fabrication-additive-metallique-](https://www.observatoire-metallurgie.fr/sites/default/files/documents/2019-04/synthese-etude-fabrication-additive-metallique-2019_1.pdf)  
586 [2019\\_1.pdf](https://www.observatoire-metallurgie.fr/sites/default/files/documents/2019-04/synthese-etude-fabrication-additive-metallique-2019_1.pdf) (accessed 27 august 2020)

587 Pawlowski L., 2008. *The science and engineering of thermal spray coatings*, Pub. John Wiley & Sons, Hoboken.  
588 <https://doi.org/10.1002/9780470754085>

589 Petsas N., Kouzilos G., Papapanos G., Vardavoulias M., Moutsatsou A., 2007. Worker Exposure Monitoring of  
590 Suspended Particles in a Thermal Spray Industry. *J. Therm. Spray Technol.* 16, 214-219.  
591 <https://doi.org/10.1007/s11666-007-9027-6>

592 Peukert W., Wadenpohl, 2001. Industrial separation of fine particles with difficult dust properties. *Powder Technol.*  
593 118(1-2), 136-148. [https://doi.org/10.1016/S0032-5910\(01\)00304-7](https://doi.org/10.1016/S0032-5910(01)00304-7)

594 Pipame France, 2017. *Futur de la fabrication additive (in French)*. ISBN:978-2-11-151552-9

595 Reijnders, L., 2006. Cleaner nanotechnology and hazard reduction of manufactured nanoparticles. *J. Clean. Prod.* 14,  
596 124-133. <https://doi.org/10.1016/j.jclepro.2005.03.018>

597 Ribalta C., Koivisto A. J., Salmatonidis A., López-Lilao A., Monfort E., Viana M., 2016. Modeling of high  
598 nanoparticle exposure in an indoor industrial scenario with a one-box model. *Int. J. Environ. Res. Public*  
599 *Health.* 16, 1695-1711. <https://doi.org/10.3390/ijerph16101695>

600 Salmatonidis A., Viana M., Perez N., Alastuey A., Sanfelix V., Monfort E., Angurel L. A., De La Fuente G. F., 2018.  
601 Exposure to process-generated nanoparticles during thermal spraying. 6th Nanosafe International Conference  
602 on Health and Safety (Grenoble, France), 5-9 november 2018

603 Salmatonidis A., Viana M., Biskos G., Bezantakos S., 2020, Particle size distributions and hygroscopic restructuring  
604 of ultrafine particles emitted during thermal spraying. *Aerosol Sci. Tech.* 54, 1359-1372.  
605 <https://doi.org/10.1080/02786826.2020.1784837>



606 Samal S., 2017. Thermal plasma technology: The prospective future in material processing, *J. Clean. Prod.* 142,  
607 3131-3150. <https://doi.org/10.1016/j.jclepro.2016.10.154>

608 Savary B., 2014. Panorama de la projection thermique en France : Résultats de l'enquête de 2012 (in french). INRS  
609 NS326. Pub. INRS, Paris. [http://www.inrs.fr/inrs/recherche/etudes-publications-](http://www.inrs.fr/inrs/recherche/etudes-publications-communications/doc/publication.html?refINRS=B.4/1.086/P2014-147/NS326)  
610 [communications/doc/publication.html?refINRS=B.4/1.086/P2014-147/NS326](http://www.inrs.fr/inrs/recherche/etudes-publications-communications/doc/publication.html?refINRS=B.4/1.086/P2014-147/NS326) (accessed 27 august 2020)

611 Savary B., 2015. Projection thermique : Procédés, dangers, population exposée et niveau d'exposition (in French),  
612 Proceeding of Mardis de Fernand Vidal – METRANEP (Paris, France). [http://www.centres-](http://www.centres-antipoison.net/paris/mfw/2015/MFW_20150630_B_Savary_Projection_Thermique.pdf)  
613 [antipoison.net/paris/mfw/2015/MFW\\_20150630\\_B\\_Savary\\_Projection\\_Thermique.pdf](http://www.centres-antipoison.net/paris/mfw/2015/MFW_20150630_B_Savary_Projection_Thermique.pdf) (accessed 27 august  
614 2020)

615 Siret B., 2001. Dépoussiérage et dévésiculage (in french). *Techniques de l'ingénieur.* j3580.

616 Stefaniak A. B., Johnson A.R., Preez S., Hammond D.R., Wells, J.R., Ham, J.E., LeBouf R.F., Martin, S.B., Duling  
617 M.G., Bowers L.N., Knepp A.K., De Beer D.J., Du Plessis J.L., 2019. Insights Into Emissions and Exposures  
618 From Use of Industrial-Scale Additive Manufacturing Machines. *Safety Health at Work.* 10(2), 229-236  
619 <https://doi.org/10.1016/j.shaw.2018.10.003>

620 Stephens B., Azimi P., El Orch Z., Ramos T., 2013. Ultrafine particle emissions from desktop 3D printers. *Atmos.*  
621 *Envir.* 79, 334-339. <https://doi.org/10.1016/j.atmosenv.2013.06.050>

622 Sousa M., Arezes P., Silva F., 2019. Nanomaterials exposure as an occupational risk in metal additive  
623 manufacturing. *J. Phys.: Conf. Ser.* 1323, 6588-6596. <http://dx.doi.org/10.1088/1742-6596/1323/1/012013>

624 Subramaniam V. D., Prasad S. V., Banerjee A., Gopinath M., Murugesan R., Marotta F., Sun X. F., Pathak S., 2018.  
625 Health hazards of nanoparticles: understanding the toxicity mechanism of nanosized ZnO in cosmetic  
626 products. *Drug Chemical Toxicology.* 42, 84-93 <https://doi.org/10.1080/01480545.2018.1491987>

627 Thermal Spray Society, 2013. Environment, Health and Safety Guidelines. Pub. ASM Thermal Spray Society,  
628 Materials Park. <http://www.asminternational.org/web/tss/technical/safety-guidelines> (accessed 27 august  
629 2020)

630 Thomas D., 2016. Costs, benefits, and adoption of additive manufacturing: a supply chain perspective. *Int. J. Adv.*  
631 *Manufac. Technol.* 85, 1857-1876. <https://doi.org/10.1007/s00170-015-7973-6>

632 Tofail S. A. M., Koumoulos E. P., Bandyopadhyay A., Bose S., O'Donoghue L., Charitidis C., 2018. Additive  
633 manufacturing: scientific and technological challenges, market uptake and opportunities. *Mater. Today*. 21,  
634 22-37. <https://doi.org/10.1016/j.mattod.2017.07.001>

635 Toma F. L., Bertrand G., Klein D., Meunier C., Begin S., 2008. Development of photocatalytic active TiO<sub>2</sub> surfaces  
636 by thermal spraying of nanopowders. *J. Nanomaterials*. 2008. <https://doi.org/10.1155/2008/384171>

637 Trompeter W. J., Ancelet T., Davy P. K., Kennedy J., 2016. Fugitive emissions from nanopowder manufacturing. *J.*  
638 *Nanopart Res.* 18(7), 203. <https://doi.org/10.1007/s11051-016-3509-8>

639 Vardelle A., Moreau C., Akedo J., Ashrafizadeh H., Berndt C. C., Oberste Berghaus J. et al., 2016. The 2016  
640 Thermal Spray Roadmap. *J. Therm Spray Technol.* 15, 1376-1440. <https://doi.org/10.1007/s11666-016-0473->  
641 x

642 Viana M., Fonseca A. S., Querol X., López-Lilao A., Carpio P., Salmatidis A., Monfort E., 2017. Workplace  
643 exposure and release of ultrafine particles during atmospheric plasma spraying in the ceramic industry. *Sci.*  
644 *Total Env.* 599-600, 2065-2073. <https://doi.org/10.1016/j.scitotenv.2017.05.132>

645 Vuoristo P., 2014. Thermal Spray Coating Processes. *Comprehensive Mater. Processing*. 4, 229-276.  
646 <https://doi.org/10.1016/B978-0-08-096532-1.00407-6>

647

648

649 **Figure captions**

650 Figure 1: Powder atomization principle

651 Figure 2: Additive manufacturing principle

652 Figure 3: Thermal spray principle

653 Figure 4: Different processes used by the French companies (CaRPE survey)

654 Figure 5: Sprayed metal-based materials used by French thermal spray companies (CaRPE survey)

655 Figure 6: Thermal spray environment (CaRPE survey)

656 Figure 7: Thermal spray dust exhaust equipment characteristics (CaRPE survey)

657 Figure 8: Personal respiratory protective equipment of workers and booth cleaning (CaRPE survey)

658 Figure 9: Achievement of emissions measurements (CaRPE survey)

659 Figure 10: Pictures of melted metal droplets and jets during a) powder atomization, b) thermal spray and c) selective  
660 laser melting processes

661 Figure 11: PM particles description

662

663 **Table captions**


664 Table 1: Questions of CaRPE survey for thermal spray companies


665 Table 2: Ducted and diffuse emissions


666 Table 3: Efficiencies, maximum gas flow and particle content of the main dust collectors (Brinkmann et al, 2016)

667 Table 4: Benefits and limitations of the main dust collectors (Brinkmann et al, 2016; Peukert et al., 2001; Hallé et al.,

668 2015; and experience from the authors)







**powder injection**

**spread particles**


**molten particles**


**plasma, flame, arc**

**substrate**


**gas**

**energy**







APS




HY OF HYAF



Wire and spraying



Flame spraying







### Main work environment




### Type of air capture around the process




### Section above the powder feeder




### Types of dust exhaust equipment




### Effectiveness of the filter media (cartridge, bag, etc.)




**Personal respiratory protective equipment carried by most of thermal spray operators**




**Operating stages when the respiratory PPE is worn**




**Class of respiratory protective equipment filters**




**Frequency of thermal spray booth cleaning**




**Main system used to clean the thermal spray booth**




### Achievement of annual or particle emission measurements




### Achievement of measurements at the level of operators (sampler on workstation)




### Achievement of ambient measurements



### Achievement of measurements outside at the dust collector exit







**PM1 (<1µm)**  
Nanoparticles, virus

**PM2.5 (<2.5µm)**  
Bacteria, mushrooms, combustion particles

**PM10 (<10µm)**  
Folken, coarse dust

**Table 1: Questions of CaRPE survey for thermal spray companies**

<p><b>Company activity</b></p>	<ul style="list-style-type: none"> <li>•How many employees use thermal spraying processes?</li> <li>•How many different thermal spray processes are you equipped with?</li> <li>•How many thermal spray booths are you equipped with?</li> <li>•What is the annual order of magnitude regarding raw material for thermal spraying (powder, wire, etc.)?</li> <li>•Which processes are you equipped with?</li> <li>•What are the sprayed metal based materials used with each process?</li> </ul>
<p><b>Emissions and dust equipment</b></p>	<ul style="list-style-type: none"> <li>•What is the main work environment in the workshop?</li> <li>•What type of air capture are you equipped with?</li> <li>•What types of dust exhaust equipment are you equipped with?</li> <li>•Do you have suction over the powder feeder (suction arm, etc.)?</li> <li>•How efficient is the filter medium of your cartridge or bag dust collector?</li> </ul>
<p><b>Personal protection</b></p>	<ul style="list-style-type: none"> <li>•What personal respiratory protection equipment most thermal spray operators wear?</li> <li>•What is the efficiency class of respiratory protective equipment filters?</li> <li>•When must PPE be worn?</li> <li>•How often do you clean the thermal spray booths?</li> <li>•How do you clean the thermal spray booths?</li> </ul>
<p><b>Emission control</b></p>	<ul style="list-style-type: none"> <li>•Are aerosols or particle emissions measured?</li> <li>•Do you take measurements at the level of operators (sampler on workstation)?</li> <li>•Do you take ambient measurements?</li> <li>•Do you take measurements out at the dust collector exit?</li> </ul>

**Table 2: Ducted and diffuse emissions [1]**

Ducted emissions	Diffuse emissions
<ul style="list-style-type: none"> <li>• process emissions released through a ventilation pipe via the process equipment</li> <li>• gas flow from energy-providing units, such as process furnaces, steam boilers, combined heat and power units, gas turbines, and gas engines</li> <li>• waste gases from emission control equipment, such as filters, incinerators/oxidisers or adsorbers, likely to contain unabated pollutants or pollutants generated in the abated system</li> <li>• tail gases from reaction vessels and condensers</li> <li>• waste gases from catalyst regeneration</li> <li>• waste gases from solvent regeneration</li> <li>• waste gases from vents from storage and handling (transfers, loading and unloading) of products, raw materials and intermediate</li> <li>• waste gases from purge vents or preheating equipment, which are used only in start-up or shutdown operations</li> <li>• discharges from safety relief devices (e.g. safety vents, safety valves)</li> <li>• exhaust air from general ventilation systems</li> <li>• exhaust air from vents from captured diffuse sources, e.g. diffuse sources installed within a facility</li> </ul>	<ul style="list-style-type: none"> <li>• process emissions from the process equipment inherent in running the plant, released from a large surface or through openings</li> <li>• non-ducted emissions (e.g. 'working losses' and 'breathing losses', when not captured and ducted) from storage equipment and during handling operations (e.g. drum filling, trucks or containers)</li> <li>• uncommon emissions, resulting from operations other than routine processing of the facility including emissions during start-up or shutdown and during maintenance</li> <li>• secondary emissions resulting from the waste handling or disposal (e.g. volatile material from sewers, waste water handling facilities or cooling water)</li> <li>• fugitive emissions (see Glossary), such as equipment leaks from pump and compressor seals, valves, flanges, connectors and others piping items, or other equipment items, such as drain or vent plugs or seals</li> </ul>



**Table 3: Efficiencies, maximum gas flow and particle content of the main dust collectors (Brinkmann et al, 2016)**

	<b>Abatement efficiency (%)</b>	<b>Waste gas flow (Nm<sup>3</sup>/h)</b>	<b>PM content (g/Nm<sup>3</sup>)</b>
<b>Settling chambers</b>	10-90	100 – 100 000	No restriction
<b>Cyclones</b>	PM <sub>&gt;50</sub> – 99 PM <sub>10</sub> – 30-90 PM <sub>2.5</sub> – 0-40 PM <sub>1</sub> – 5	1 – 100 000	1 – 16 000
<b>Electrostatic precipitator</b>	99 PM <sub>2.5</sub> – 97-99.2 PM <sub>1</sub> – 97	1 800 – 2 000 000	1 - 110
<b>Fibrous media</b>	99 – 99.9	300 – 1 800 000	0.1 - 230
<b>Absolute filter</b>	99.999 PM <sub>0.1</sub> – 99.999 PM <sub>0.01</sub> – 99.99	100 - 300	1 - 30
<b>Wet dust scrubber (spray tower)</b>	PM <sub>10</sub> – 70 -99	2 500 – 170 000	No restriction

**Table 4: Benefits and limitations of the main dust collectors (Brinkmann et al, 2016; Peukert et al., 2001; Hallé et al., 2015; and experience from the authors)**

	<b>Benefits</b>	<b>Limitations</b>
<b>Settling chambers</b>	<p>Simple construction, no moving part hence low maintenance and low operating costs</p> <p>Very low pressure drop</p> <p>Suitable for higher temperatures</p> <p>Low investment costs</p> <p>Low energy consumption</p> <p>Can be applied to processes with large fluctuations, e.g. with high and low temperatures</p>	<p>Poor removal efficiency, especially for small particles (<b>below 50 µm</b>)</p> <p>Unsuitable for sticky particles</p> <p>Not suitable when the density difference between gas and particulates is small</p> <p>Relatively large equipment</p> <p><b>Decrease of efficiency for low concentration at the inlet</b></p>
<b>Cyclones</b>	<p>Simplicity of the installation</p> <p>Recovery of raw material</p> <p>No moving parts, hence few maintenance requirements and low operating costs</p> <p>Low investment <b>and maintenance</b> costs</p> <p>Dry collection and disposal, except for wet cyclones</p> <p>Relatively small space requirements</p> <p><b>Low consumption of energy</b></p> <p><b>Relatively low pressure drop</b></p> <p><b>High density of particle flows can be treated</b></p>	<p>Relatively low PM abatement efficiency, particularly <b>below PM<sub>10</sub></b>. <b>In the current regulatory framework, it should be used solely as a pre dust-removal system</b></p> <p><b>The higher the efficiency the higher the pressure drop and the energy consumption</b></p> <p>Axial entry cyclones cannot be used with particles likely to cause excessive erosion or clogging of the vanes in the inlet</p> <p>Unable to handle sticky or tacky materials</p> <p>Emissions to waste water with wet cyclones</p> <p>Noise</p> <p><b>Regular cleaning necessary to avoid self-heating risk with accumulation of combustible dusts</b></p>

<p><b>Electrostatic precipitator</b></p>	<p>High abatement efficiency (&gt; 97 %) even for small sized particles (high efficiency until 10 nm) and high concentration of particles (efficiency can be increased by adding fields or zones)</p> <p>Capacity of treatment of important inlet gas flows</p> <p>Low maintenance costs and possibility to work at temperatures higher than 300°C</p> <p>Low energy consumption</p> <p>Low-pressure drop, hence energy requirement tends to be low (in some applications, an induced or forced draft fan is needed to overcome system pressure drop)</p> <p>Possibility to work under vacuum</p> <p>Suitable for a wide range of temperatures, pressures and gas flows</p> <p>Dust can be removed dry, making reuse possible (for dry ESP)</p> <p>Partial removal of acid fumes (for wet ESP)</p> <p>Wet ESPs can abate sticky particles, mists and highly resistive or explosive dusts</p> <p>At a voltage of &gt; 50 kV, abatement efficiency is independent of the residence time, enabling more compact manufacturing (for wet ESP)</p>	<p><b>High initial investment costs</b></p> <p>Ozone can be formed by the electrodes, which be a source of environmental pollution</p> <p>Less suited for processes with varying gas streams, temperatures or dust concentrations. However, it can be offset by automatic adjustments. Varying operational conditions is easy, if the installation is designed for the worst case situation.</p> <p>Re-entrainment can be a problem due to high gas velocities, poor rapping or poor gas flow</p> <p>Sensitive to maintenance and settings</p> <p>Relatively large <b>equipment size</b></p> <p>Highly qualified staff is required</p> <p>Special cautions to protect staff from the high voltage (<b>electrical hazards</b>)</p> <p><b>Dry ESP must be avoided with combustible dust, as it generated dust explosion risks. Pre-combustion of the dust can be an option before ESP treatment.</b></p> <p>The abatement capacity depends on the <b>electrical</b> resistivity of dust particles (with dry ESPs)</p> <p>Dry ESPs not recommended for the removal of sticky or moist particles</p>
------------------------------------------	----------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------	--------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------

		<p>Corrosion near the top of the wires due to air leakage and acid condensation, which is also an issue with wet ESPs (although acid gases are also absorbed by the water)</p> <p>Wet ESP is adapted to combustible/ explosible dust provided that dust does not react with the liquid phase (e.g. some metallic powder that tend to produce hydrogen when in contact with water). Protection measures must be also implemented (explosion vent, earthing of the equipment to avoid electrostatic discharges, regular cleaning is also necessary to avoid the creation oof sparks between the electrodes). Also all electrical safety measures must be correctly implemented.</p> <p>Wet ESPs are relatively expensive and require post-treatment of sludge water</p>
<p><b>Fibrous media</b></p>	<p>In general, fabric filters provide high abatement efficiencies for coarse and fine particles</p> <p>Efficiency and pressure drop of continuously cleaned filters are relatively unaffected by large changes in inlet dust loads</p> <p>Dust is sorted dry without using consumables.</p> <p>The separated dust might be reused in the preceding process or recycled</p> <p>Residual emissions are virtually independent of the intake concentration</p> <p>Relatively simple operation</p>	<p>Fabric filters are not suitable for wet or sticky dusts because of the risk of filter clogging</p> <p>Heating the waste gas stream prevents condensation of fluid on the ceramic filters</p> <p>Static electricity may hinder the cake from being removed from the fabric</p> <p>Big size of the equipment</p> <p>Reverse air bag filter system requires numerous mechanical moving pieces which can be then source of failures. It then needs</p>

	<p>Reliability</p>	<p>regular maintenance. On the contrary air-pulse filters are much easier to maintain.</p> <p>Filters must be antistatic (not claimed as antistatic but truly antistatic) and correctly earthed to avoid electrostatic discharges that could ignite explosible dusts</p> <p>High clogging by ultrafine particles</p>
<b>Absolute filter</b>	<p>Abatement of submicron particles of fine dust is possible</p> <p>Very high abatement efficiency with very low residual emission</p> <p>Outlet air is very clean and can flow within the plant</p> <p>Modular structure</p> <p>Not sensitive to small fluctuations in the waste gas stream</p> <p>Relatively simple operation</p> <p>Usually not sensitive to corrosion problems</p>	<p>Care has to be taken with explosive hazards</p> <p>High maintenance and frequent filter replacement required</p> <p>Not suitable for the abatement of wet dust</p> <p>Not suitable for high dust loads (except if prefiltration is carried out)</p> <p>Glass fiber medium is not suitable for waste gases which contain alkalis</p> <p>High clogging by ultrafine particles</p>
<b>Wet dust scrubber</b>	<p>Can handle gas streams which contain flammable and explosive dusts with low risk</p> <p>Reasonable size of the equipment</p> <p>Can handle both gaseous and particulate pollutants</p> <p>Good efficiency of abatement for particles below 10 <math>\mu\text{m}</math></p> <p>Possibility to collect sticky particles</p> <p>Provides cooling for hot gases</p> <p>Corrosive gases can be neutralized</p>	<p>Significant water usage and generation of waste water. The higher the efficiency of abatement, the higher the consumption of water and energy</p> <p>High maintenance costs due to corrosion and erosion issues</p> <p>Risk of plugging for treatment of high concentration of particles in the flow</p> <p>High pressure drops required for an efficient treatment</p>

	Simultaneous removal of dust and inorganic compounds	<p>Waste (or by-product if reused or recycled) collected wet</p> <p>Protection against freezing required</p> <p>Collected PM may be contaminated and/or not recycled</p> <p>Off-gas may require reheating to avoid visible plume</p> <p><b>It tends to minimize the risk of explosion or even eliminate the risk of fire and explosion, unless of course dust is reactive with the liquid phase such as some metallic dust that may form hydrogen in the presence of water.</b></p>
--	------------------------------------------------------	-------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------